


PL988



APPLICATION

PL988 is a multipurpose turf solution designed to withstand high-traffic use. Its short-pile, texturized polyethylene construction is engineered for long-lasting, low-maintenance performance. The 5mm polyurethane foam backing provides added cushioning when installed over concrete or a compacted aggregate base, and this turf is suitable for both indoor and outdoor use.

PROPERTY	DESCRIPTION
Primary/Stalk Yarn Type:	Polyethylene
Secondary/Thatch Yarn Type:	N/A
Yarn Cross Section:	Texturized Polyethylene
Standard Color(s)*:	Field
UV Stabilized:	Yes
Fabric Construction:	Tufted
Primary Backing:	ArmorLoc™ 3L Stabilized Woven PP/PET Multilayer
Coating Type(s):	5mm Polyurethane Foam
Perforations:	Not Recommended
Yarn Denier/Ends:	5600/8
Pile Height:	3/4"
Face Weight:	48 oz/yd ²
Fabric Width:	15 ft.



 **ArmorLoc™ 3L**



*Custom colors available upon request

200 Howell Dr. Dalton GA 30721


www.cpturf.com

800.564.4492


 **CONTROLLED**
PRODUCTS

PL988

FINISHED FABRIC	ENGLISH SYSTEM		METRIC SYSTEM		ASTM TEST
Nominal Specification	Value	Units	Value	Units	Method
Pile Height (Nominal)	.75	In.	19	mm.	D-5823
Face Weight	48	oz/yd ²	1,627	g/m ²	D-5848
Total Fabric Weight	133	oz/yd ²	4,509	g/m ²	D-5848
Primary Backing Weight	7	oz/yd ²	237	g/m ²	D-5848
Secondary Coating Weight	78	oz/yd ²	2,645	g/m ²	D-5848
Tuft Bind	>10	lbs.	>4.5	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-5034
Lead Content	<50	ppm	<50	ppm	F-2765
Total Yarn Linear Density	5,600	Denier	6,216	D-Tex	D-1577
Tensile Strength	8	lbs.	3.6	Kg.	D-5034
Machine Gauge	0.1875	In.	0.5	Cm.	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Fiber Thickness	–	–	100	microns	None



CURB



EQUIPMENT

It is the policy of Controlled Products to continuously improve their line of products. Therefore, Controlled Products reserves the right to change, modify or discontinue systems, specifications and accessories of all products at any time without notice or obligation to purchaser.